

1104 - AB-3 OVERLAND PARK MODIFIED

1104.1 DESCRIPTION

AB-3 Overland Park Modified shall be supplied in accordance with Section 1104 of the Standard Specifications, except as otherwise modified herein.

1104.2 MATERIALS

Paragraph 1104.2(a) composition shall be modified so that the AB-3 Overland Park modified shall consist of 100% limestone or dolomite produced by mechanical crushing.

Table 1104-1: Gradation and Plasticity of Aggregates for Aggregate Base Construction shall be modified so that the AB-3 Overland Park modified shall have the gradation shown on line AB-3; however, the P.I. shall be between 0 and 5 and the liquid limit shall be 25 maximum.

The material shall be mixed with water in a stationary plant, before delivery to the project site, to obtain the moisture content as directed by the City Engineer.

1104.3 CERTIFICATION OF THE MATERIAL

The Contractor shall submit with the delivery of the material to the project, a certificate indicating the gradation, plasticity index, and the moisture-density relationships of the material using ASTM D698 complies with the above material specification.