



591 Glendale Ave Greenville AL 36037

Phone: 334-213-2995 Fax: 334-277-2996

Test Report

Material: Ozark Materials, LLC Paint
Specification: TTP 1952 F Type II Yellow
Product Number: 25214 (Overland Park, KS.)
Batch Number: Submittal

TEST METHODS

SPECIFICATION

RESULT

Physical Characteristics

% pigment	60-62%	61.42%
Flexibility	Pass	Pass
Viscosity	80-90	87
Dry Time (D-711) (.015)	10 max	7'
Bleeding	.95 min	0.986
Fineness of Grind	3 min	4
Directional Reflectance (.015)	50 min	55.75%
Contrast Ratio (.005)	.92 min	0.99
Color (x)	.4750-.5200	0.4858
(y)	.4330-.4750	0.4446
VOC	150 Grams per Liter (Max)	88 / G/L

I certify to the best of my knowledge that this material complies with all requirements of
TTP 1952 F Waterborne Traffic Marking Paint

David Hayes

Representative