



591 Glendale Ave Greenville AL 36037

Phone: 334-213-2995 Fax: 334-277-2996

Test Report

Material: Ozark Materials, LLC Paint
Specification: TTP 1952 E Type II White
Product Number: 15214 (Overland Park, KS.)
Batch Number: Submittal

TEST METHODS

SPECIFICATION

RESULT

Physical Characteristics

% pigment	60-62%	61.55
Flexibility	Pass	Pass
Viscosity	80-90	86
Dry Time (D-711) (.015)	10 max	8'
Bleeding	.95 min	0.99
Fineness of Grind	3 min	4
Freeze-Thaw	+/- 5 KU	Pass
Directional Reflectance (.015)	85 Min	90.04
Contrast Ratio (.005)	.92 min	0.99
Heat Stability	150 Grams per Liter (Max)	90 G/L
VOC		

I certify to the best of my knowledge that this material complies with all requirements of
TTP 1952 E Waterborne Traffic Marking Paint

David Hayes

Representative