



591 Glendale Ave Greenville AL 36037

Phone: 334-213-2995 Fax: 334-277-2996

## Test Report

Material: Ozark Materials, LLC Paint  
Specification: TTP 1952 E Type II Yellow  
Product Number: 25214 (Overland Park, KS.)  
Batch Number: Submittal

### TEST METHODS

### SPECIFICATION

### RESULT

#### Physical Characteristics

% pigment	60-62%	61.42
Flexibility	Pass	Pass
Viscosity	80-90	87
Dry Time (D-711) (.015)	10 max	7'
Bleeding	.95 min	0.986
Fineness of Grind	3 min	4
Directional Reflectance (.015)	50 min	55.75%
Color (x)	.4750-.5200	0.4858
(y)	.4330-.4750	0.4446
VOC	150 Grams per Liter (Max)	88 G/L

---

I certify to the best of my knowledge that this material complies with all requirements of  
TTP 1952 E Waterborne Traffic Marking Paint

---

*David Hayes*

Representative